About OMICS Group

OMICS Group International is an amalgamation of Open Access publications and worldwide international science conferences and events. Established in the year 2007 with the sole aim of making the information on Sciences and technology 'Open Access', OMICS Group publishes 400 online open access scholarly journals in all aspects of Science, Engineering, Management and Technology journals. OMICS Group has been instrumental in taking the knowledge on Science & technology to the doorsteps of ordinary men and women. Research Scholars, Students, Libraries, Educational Institutions, Research centers and the industry are main stakeholders that benefitted greatly from this knowledge dissemination. OMICS Group also organizes 300 International conferences annually across the globe, where knowledge transfer takes place through debates, round table discussions, poster presentations, workshops, symposia and exhibitions.

About OMICS Group Conferences

OMICS Group International is a pioneer and leading science event organizer, which publishes around 400 open access journals and conducts over 300 Medical, Clinical, Engineering, Life Sciences, Phrama scientific conferences all over the globe annually with the support of more than 1000 scientific associations and 30,000 editorial board members and 3.5 million followers to its credit.

OMICS Group has organized 500 conferences, workshops and national symposiums across the major cities including San Francisco, Las Vegas, San Antonio, Omaha, Orlando, Raleigh, Santa Clara, Chicago, Philadelphia, Baltimore, United Kingdom, Valencia, Dubai, Beijing, Hyderabad, Bengaluru and Mumbai.

4th International Conference on Clinical & Experimental Ophthalmology

Equilibrium Binding Interactions Between Lotrafilcon A Soft Contact Lenses And The Two Prostaglandin Anti-glaucoma Drugs Bimatoprost And Tafluprost



Richard Kenley, Ph.D. 16 July 2014

PRESENTATION OVERVIEW

- Prostaglandin Drugs Description
- Lotrafilcon Lens Description
- Equilibrium Binding Equations
- Methods
- Results
- Conclusions

Prostaglandin Drugs

Bimatoprost

- LogP = 3.2
- 300 μg/mL plus sodium chloride, sodium phosphate, and citric acid in water

Tafluprost

- LogP = 4.5
- 15 µg/mL plus glycerol, sodium dihydrogen phosphate, disodium edetate, polysorbate 80, and water

Lotrafilcon Soft Contact Lens

- block copolymer of poly(dimethylsiloxane) and poly(perfluoroether)
- highly porous and highly permeable
- rapid absorption of various drugs from solution into Lotrafilcon A lens material



Equilibrium Binding

- $E_B = M_P * V_S / W_P * M_S$
 - $E_B = Equilibrium Binding Constant$
 - $-M_p$ = Solute Mass Bound to Polymer (lens)
 - $-V_S = Volume of Solution$
 - $-W_p = Polymer (lens) Weight$
 - $-M_S$ = Solute Mass in Solution Phase
- $1/F_{\text{soln}} = E_B * (W_P/V_S) + 1$
 - $-F_{soln} = [Solute]_{obs} \div [Solute]_{init} = Fraction of Initially-added Solute in Solution Phase at equilibrium$

Methods

- Incubate lens pieces with drug in solution (formulation)
- Vary Solution Volume with constant mass of lens pieces
- Assay for [Drug] by UPLC
- 25 or 37 C
- Marker Compounds With Known LogP Values
 - Dimethyl, Diethyl, and Dipropryl Phthalates (DMP, DEP, DPP)
 - Methyl, Ethyl, and Propyl Esters of p-Hydroxybenzoic Acid (MePB, EtPB, and PrPB)
 - Incubated in PBS with lens pieces and analyzed by UPLC

Phthalates Vs Time and W_p/V_s Ratio

Solute	[Solute] _{Init} , mg/mL	[Solute] _{obs} , mg/mL	W _P , mg	V_{S} , mL	Temp °C	Time, hr	100*F _{soln}
DMP	0.30	0.070	18.2	0.1	37	1	23
DMP	0.30	0.108	18.0	0.2	37	1	36
DMP	0.30	0.148	20.5	0.3	37	1	49
DMP	0.30	0.156	20.2	0.4	37	1	52
DMP	0.30	0.129	17.9	0.2	37	0.25	43
DMP	0.30	0.118	21.2	0.2	37	0.5	39
DMP	0.30	0.122	21.1	0.2	37	1	41
DMP	0.30	0.127	18.5	0.2	37	2	42
DEP	0.30	0.014	18.2	0.1	37	1	4.7
DEP	0.30	0.029	18.0	0.2	37	1	10
DEP	0.30	0.051	20.5	0.3	37	1	17
DEP	0.30	0.056	20.2	0.4	37	1	19
DEP	0.30	0.050	17.9	0.2	37	0.25	17
DEP	0.30	<lod< td=""><td>21.2</td><td>0.2</td><td>37</td><td>0.5</td><td>*</td></lod<>	21.2	0.2	37	0.5	*
DEP	0.30	0.034	21.1	0.2	37	1	11
DEP	0.30	0.036	18.5	0.2	37	2	12
DPP	0.30	<lod< td=""><td>18.2</td><td>0.1</td><td>37</td><td>1</td><td>*</td></lod<>	18.2	0.1	37	1	*
DPP	0.30	0.002	18.0	0.2	37	1	0.6
DPP	0.30	0.008	20.5	0.3	37	1	2.8
DPP	0.30	0.006	20.2	0.4	37	1	2.1



Results $-E_B$ For Bimatoprost

Table 1 Equilibrium Binding Results and Computations for Bimatoprost (In Topical Ophthalmic Solution) Interactions with Lotrafilcon A Lens Material*

Sample	V _s , mL	W _p , mg	$\mathbf{F_{soln}}^{\dagger}$	W_p/V_s	1/F _{soln}
1-1	0.10	15.38	0.239	154	4.19
1-2	0.10	17.07	0.244	171	4.10
1-3	0.10	17.24	0.202	172	4.94
2-1	0.20	16.71	0.504	83.6	1.99
2-2	0.20	16.70	0.348	83.5	2.88
2-3	0.20	16.99	0.345	85.0	2.90
3-1	0.30	15.62	0.473	52.1	2.11
3-2	0.30	15.80	0.513	52.7	1.95
3-3	0.30	16.20	0.470	54.0	2.13
4-1	0.40	15.23	0.466	38.1	2.14
4-2	0.40	16.03	0.492	40.1	2.03
4-3	0.40	15.77	0.482	39.4	2.07
	Mean =	16.23		Slope** =	0.0194
	%RSD =	4.27%		Intercept** =	1.13
				$RSQ^{**} =$	0.907

^{*} At 37 °C, incubation interval = 60 min. † See equation (2). ** Slope, intercept and RSQ per equation (5).



E_B For Tafluprost


Table 1 Equilibrium Binding Results and Computations for Tafluprost (in Saflutan Drug Product) Interactions with Lotrafilcon A Lens Material*

Sample	V _s , mL	W _p , mg	$\mathbf{F_{soln}}^{\dagger}$	W_p/V_s	1/F _{soln}
1-1	0.20	18.96	0.198	94.8	5.04
1-2	0.20	19.88	0.111	99.4	9.03
1-3	0.20	19.09	0.199	95.5	5.03
2-1	0.40	19.35	0.245	48.4	4.09
2-2	0.40	18.34	0.227	45.9	4.40
2-3	0.40	17.97	0.316	44.9	3.16
3-1	0.60	17.6	0.327	29.3	3.05
3-2	0.60	18.51	0.340	30.9	2.94
3-3	0.60	19.83	0.342	33.1	2.93
4-1	0.80	17.77	0.416	22.2	2.41
4-2	0.80	19.13	0.509	23.9	1.96
4-3	0.80	17.33	0.659	21.7	1.52
	Mean =	18.6		Slope** =	0.0575
	%RSD =	4.6%		Intercept** =	-0.038
				$RSQ^{**} =$	0.745


^{*} At 37 °C for 60 min. † See equation (2). ** Slope, intercept and RSQ per equation (5).

1/F_{soln} vs. W_p/V_s Ratio for Phthalates

1/F_{soln} vs W_p/V_s Ratio for Phthalate Esters at 37 C




1/F_{soln} W_p/V_s Ratio for Parabens




F_{soln} vs V_s/W_p Ratio for Tafluprost at 25 and 37 C

FSoln vs Vs/Wp Ratio Tafluprost Initial = 0.015 mg/mL





Log(E_B) vs LogP





Conclusions

- The fraction of either bimatoprost or tafluprost that binds to Lotrafilcon A increases with increasing lens:solution (w/v) ratio.
- Both drugs partition very rapidly (< 15 min) and extensively into Lotrafilcon A lens
- Calculate that a 60-µL dose volume applied to a single contact lens yields 16% of initially bimatoprost remaining in solution, but only 6% of tafluprost remains in solution
- Advise contact lens wearers to remove the lenses before administering either prostaglandin drug
- Hydrophobic interactions are important but not the only significant factor controlling drug binding to Lotrafilcon A

Let Us Meet Again

We welcome you all to our future conferences of OMICS Group International

Please Visit:

www.omicsgroup.com

www.conferenceseries.com

http://ophthalmology.conferenceseries.com/

